

AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claims 1-10 (Cancelled).

Claim 11 (Currently amended): A process for producing a flatted coating ~~which comprises~~ comprising the steps of:

- (a) introducing into a self-curing or radiation-curing coating system ~~at least one~~ a liquid dimerdiol (meth)acrylate, in an amount effective to flat the coating system, said dimerdiol (meth)acrylate having a degree of esterification of at least 50%, to form a flatted coating system;
 - (b) applying a coating of ~~the~~ said flatted coating system to a substrate comprising glass; and
 - (c) curing the coating,
- wherein the cured coating is flatted with respect to the same coating without said ~~at least one~~ dimerdiol (meth)acrylate.

Claim 12 (Previously presented): The process of claim 11, wherein, from 1% to 25% by weight of the dimerdiol (meth)acrylate is added to the coating system based on the weight of the coating system.

Claim 13 (Previously presented): The process of claim 11, wherein, the dimerdiol (meth)acrylate has a degree of esterification of at least 80%.

Claim 14 (Previously presented): The process of claim 11, wherein, the flatted coating system further comprises a solid flattening agent.

Claim 15 (Previously presented): The process of claim 12, wherein, the dimerdiol (meth)acrylate has a degree of esterification of at least 80%.

Claim 16 (Previously presented): The process of claim 12, wherein the flattened coating system further comprises a solid flattening agent.

Claim 17-18 (Cancelled):

Claim 19 (Currently amended): A method for flattening a substrate surface comprising glass, comprising the steps of applying a self-curing and/or radiation-curing coating system to a substrate surface comprising glass, and curing, wherein said self-curing and/or radiation-curing coating system comprises at least one a liquid dimerdiol (meth)acrylate having a degree of esterification of at least 50%, in an amount effective to flat the cured coating, and wherein said cured coating is flattened with respect to the same coating without said ~~at least one~~ dimerdiol (meth)acrylate.

Claim 20-21 (Cancelled):